

Product Information

ACEMATT® OK412

Characteristic physico-chemical data^{*)}

Properties and Test Methods	Units	Value
Loss on drying 2h at 105 °C following ISO 787-2	%	6
Loss on ignition¹⁾ 2h at 1000 °C following ISO 3262-1	%	13
pH value 5% in water following ISO 787-9	–	6
Sulfate content as SO₄ IR spectrometrically Internal method	%	1
Particle size, d50 Laser diffraction following ISO 13320-1	µm	6.0
Surface treatment		organic
Tamped density not sieved following ISO 787-11	g/l	130
Density following ISO 787-10	g/cm ³	1.9
Oil absorption following ISO 787-5	g/100g	220
SiO₂ content²⁾ following ISO 3262-19	%	98
Package size (net)	kg	15

1) based on dried substance

2) based on ignited substance

*) The given data are typical values.
Specifications on request.

ACEMATT® Matting agents are high performance silica developed for a variety of applications in Paints & Coatings.

ACEMATT® OK 412 is an organically surface treated, easily dispersible matting agent for general applications.

Application and characteristics

This matting agent allows exceptional surface characteristics with excellent slip-effect, also in pigmented coatings. As a result of its outstanding suspension behavior, it is especially suitable for use in clear coats.

Registrations

EINECS (Europe)	registered
USA (TSCA)	registered
Canada (DSL)	registered
Australia (AICS)	registered
Korea (ECL)	registered
Japan (ENCS)	registered
Philippines (PICCS)	registered
China (IECS)	registered
New Zealand	registered

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.



**Europe/Middle-East/
Africa/Latin America**
Evonik Degussa GmbH
Inorganic Materials
Weißfrauenstr. 9
60287 Frankfurt am Main
Germany
PHONE +49 69 218-2613
FAX +49 69 218-62613
ask-si@evonik.com

NAFTA
Evonik Degussa Corporation
Inorganic Materials
379 Interpace Parkway
P.O. Box 377
Parsippany, NJ 07054-0677
USA
PHONE +1 888 745-4227
FAX +1 732 981-5310
ask-si-nafta@evonik.com

Asia / Pacific
Evonik Degussa (SEA) Pte. Ltd.
Inorganic Materials
3 International Business Park
#07-18 Nordic European Centre
Singapore 609927
PHONE +65 6 890-6031
FAX +65 6 890-6872
ask-si-asia@evonik.com

www.evonik.com